

TECHNICAL DATA SHEET 'FO-POXY (Cu)'

DESCRIPTION : Good electric conductance and has an ability for repairing and rebuilding of damaged copper parts and equipments. This compound is machinable.

APPLICATION : Repair of damaged copper part & for imparting good electric conductance coating.

PROPERTIES :

CURE TIME	(HRS.)	-	30
COMPRESSIVE STRENGTH	(KGS/CM ²)	-	1220
TENSILE SHEAR STRENGTH	(KGS/CM ²)	-	150
FLEXURAL STRENGTH	(KGS/CM ²)	-	600
HARDNESS	(SHORE D)	-	90

TEMP. RANGE : UPTO 175°C

CHEMICAL REACTIVITY : Doesn't react with common industrial gases, acids, reagents and solvents.

ADDITIONAL INFORMATION : Can be prepared as per client specification.
Coverage Area : 1 sq.mtr. / Kg for 0.4 mm product thickness

MANUFACTURED BY :

AQUADRA FORSPEC PVT. LTD.

2-A, Tower A, Viceroy Park, Kandivli (E), Mumbai - 400 101

Tel : +91 9820 393 292 / +91 98209 90182

E-mail : aquadraforspec@gmail.com

URL : <http://www.aquadra.in>